

**TEST REPORT
HRN EN 14342:2013 (EN 14342:2013)**

No.: 115-1338-02-2018

Date: 29.05.2018.

Testing location:

Euroinspekt - drvokontrola d.o.o.

Laboratory for testing forestry, wood industry and construction
products
Svačićeva bb
HR-35000 Slavonski Brod
tel/fax: ++385 35 446-407

GENERAL INFORMATION:

Applicant:	TARA d.o.o.	Desimirovac	Serbia - 34321 Kragujevac
Product name / type:	Solid wood parquet - oak	Solid parquet elements with grooves and/or tongues	
Manufacturer:	TARA d.o.o.	Product origin:	Serbia

TEST RESULT:

HRN EN 14342:2013 - Wood flooring - Characteristics, evaluation of conformity and marking - Paragraph 4.8 - Biological durability	Dur. of healthy wood	1
	Fungus	2-4
	Worms	D
	Termites	M

Report appliance: This document refers only to the tested sample by mentioned applicant and manufacturer of final product and it is not transferable to other legal or private persons.

Duplication of this document is strictly forbidden without written approval from Euroinspekt-drvokontrola d.o.o.



1. Requirement:

Determination of biological durability according to:

HRN EN 14342:2013, paragraph 4.8

2. Laboratory test results:

Laboratory product marking: 000091-000-17

Date of admittance of the sample: 25.09.2017.

Admittance and testing according to
Test Warrant no.: 1482/17

Product sampling performed
according to Sampling Protocol
no.: 035-GS/17

3. Description of the sample:

Parquet elements made of oak, shaped according to HRN EN 13226:2010, oiled surfaces.

Photo of the sample:



Determination of biological durability according to record no.: 000091-000-17

Following the requirement for determination of biological durability of wood floor covering, it is determined:

4. Basic product information:

Wood flooring type:	Solid parquet el. with grooves and/or tongues
Purpose:	Laying on a flat dry base
Binding with the base:	Gluing
Space:	Dry closed space
Surface finishing:	Oiled surface
Thickness mm:	20
Wood species:	Oak
Botanical name:	Quercus robur/ Quercus petraea
Standard marking:	QCXE
Wood moisture %:	-

5. Determination of biological durability according to HRN EN 14342:2013, paragraph 4.8

Using basic product standard HRN EN 14342:2013, paragraph 4.8 and Annex A, it is determined that for parquet elements biological durability is classified with reference to hazard classes according to:

HRN EN 335:2013-Durability of heathy wood

By laying the wood flooring into dry closed space, hazard class is determined:

1

Determination of wood species

By macro analysis the species oak is determined.

Density of oak wood according to HRN EN 350:2016, is 670-710-760 kg/m³.

Using basic product standard HRN EN 14342:2013, paragraph 4.8 and Annex A, it is determined that the natural durability of wood without sapwood, according to HRN EN 350:2016 Durability of wood and products based on wood is:

- fungus	2-4
- worms (anobium)	D
- termites	M


Sapwood is not permanent without protective treatments.

6. Tabular class of biological durability is:

2-4/D/M

END OF REPORT

General Manager, CEO:



Mr. sc. Mladen Komac, dipl. ing.