

TEST REPORT
HRN EN 14342:2013 (EN 14342:2013)

No. 115-1338-21-2018

Date: 29.05.2018.

Testing location:

Euroinspekt - drvokontrola d.o.o.

Laboratory for testing forestry, wood industry and construction
products
Svačićeva bb
HR-35000 Slavonski Brod
tel/fax: ++385 35 446-407

GENERAL INFORMATION:

Applicant:	TARA d.o.o.	Desimirovac	Serbia - 34321 Kragujevac
Product name / type:	Mosaic parquet oak - oiled 15 mm	Mosaic parquet elements	
Manufacturer:	TARA d.o.o.	Product origin:	Serbia

TEST RESULT:

HRN EN 14342:2013 - Wood flooring - Characteristics, evaluation of conformity and marking - Paragraph 4.6 - Slipperiness

63 USRV

Report appliance: This document refers only to the tested sample by mentioned applicant and manufacturer of final product and it is not transferable to other legal or private persons.

Duplication of this document is strictly forbidden without written approval from Euroinspekt-drvokontrola d.o.o.



1. Testing requirements

Determination of slipperiness properties following HRN EN 14342:2013, in accordance with:

HRS CEN/TS 15676:2010 - Resistance to slipperiness - Pendulum test

2. Laboratory test results:

Laboratory product marking: 000110-000-17

Date of admittance of the sample: 25.09.2017.


Admittance and testing according to
Test Warrant no.: 1482/17

Product sampling performed according to Sampling Protocol no.: 035-GS/17

3. Description of the sample

Mosaic parquet elements are made of oak for top and middle layer, base layer is made from linden veneer panel, surface oiled.

Photo of the sample:



Determination of slipperiness properties: 000110-000-17

Following the requirement for determination of slipperiness properties of lacquered wood flooring,

4. Basic product information:

Wood flooring type:	Mosaic parquet elements
Finishing:	Oiled
Purpose:	Laying on a flat dry base
Binding with the base:	Gluing
Thickness mm:	15
Wood species:	Oak
Botanical name:	Quercus robur/Quercus petraea
Standard marking:	QCXE
Wood moisture %:	-

5. Using basic product standard HRN EN 14342:2013, paragraph 4.6, it is determined that slipperiness for parquet

Using basic product standard HRN EN 14342:2013, paragraph 4.6, it is determined that slipperiness for parquet elements is classified following the method from HRS CEN/TS 15676:2010.

Determined slipperiness properties:

- in dry condition (maintainance with water)

On the base of laboratory testing which was performed according to

HRS CEN/TS 15676:2010, slipperiness result is: 63 USRV

END OF REPORT



General Manager, CEO:

Mr.sc. Mladen Komac, dipl.ing.